

RIDGE BRICK

A universal, oversized brick shape with a textured riven surface. Slightly chamfered edges. Use as a field paver or as a border for any Ridge product.



paver-shield™ pavers

paver-shield™ has a tight, smooth surface texture and will not expose heavy aggregate as it wears. Ultra-dense surface has more color and more protection. Nicolock has color from top to bottom throughout the paver ensuring a lifetime of beauty. Iron oxide pigments are **guaranteed not to fade!**

USE FOR:


- WALKWAYS
- DRIVEWAYS
- BORDERS
- PATIOS
- POOL DECKS
- COURTYARDS

Ridge Brick | Color: Travertina



RIDGE BRICK

WIDTH	LENGTH	THICKNESS	PCS / SF	SF / PALLET	PCS / PALLET	LBS / PALLET
4 1/2"	9"	2 3/8"	3.63	110	400	2,950



Adobe Blend



Autumn Blend*




Brown



Cappuccino Blend*



Caramel Tan*



Charcoal



Chesapeake Blend*



Crab Orchard Blend*



Golden Brown Blend




Granite City Blend



Graphite Pearl Blend*




Lilac Blend



Marble Blend*



Mocha Blend



Oceanic Blue*



Oyster Blend*



Pennsylvania Blue**



Raven*



South Bay Blend*



Travertina*



Westchester Blend




*Premium Colors

**Deluxe Colors


INSTALLATION GUIDELINES: SAND

After excavation, compact the sub grade and install a woven separation fabric if needed. Spread and compact a base of clean, dense graded aggregate (road base). Typical compacted base thickness is 4-6" for pedestrian applications. Pavers are set on a loosely screened 1" bed of graded, clean concrete sand. Maintain a joint size of 1/16" – 3/16". When pavers are set, compact paving stones into sand with mechanical plate vibrator. Joint sand may be spread over paving stones during compaction. Installed pavers should be set 1/8" to 1/4" above final elevations to compensate for any potential settlement. Spread clean dry sand over surface and broom sweep to fill joints. Run vibrator one final time after filling joints.

CROSS-SECTION OF TYPICAL INSTALLATION



NICOLOCK PAVING STONE 1"-31/8" THICK



NOTE: All measurements are nominal. Variance in square footage or linear footage coverage can be up to 5% depending on joint width. The possible occurrence of efflorescence does not affect the structural integrity of the product. Efflorescence is a normal occurrence in concrete products and will dissipate with normal weathering. The use of concrete as a base or setting bed may increase the possibility of efflorescence.

CAUTION: Always use a plate compactor with a pad when installing any textured paving stone.



Corporate HQ: 612 Muncy Avenue | Lindenhurst | NY | 11757 | 631.669.0700 | nicolock.com

